

# Elvacite® 4028

## Acrylic Resin

Elvacite® 4028 is designed for use in screen printing inks but can be used in a variety of ink formulations. It can also be of use in PVC finishing lacquers and plastic coatings. Films formed from Elvacite® 4028 are hard and flexible with a good balance of properties.

Typical Properties <sup>a</sup>	
Appearance	Solid bead
Glass Transition Temp, onset (calculated)	89°C
Molecular Weight (Mw)	95,000
Acid Number (mg KOH/g Resin)	0

*a) Typical physical properties listed are approximate values and should not be considered manufacturer's release specifications. Manufacturer's release specifications are subject to change without notice, please contact your Elvacite® representative for the latest product specification details.*

## Preparing Solutions

Elvacite® resins dissolve at room temperature but require constant agitation to prevent solvent-swollen granules of polymer from forming agglomerates and sticking to the walls of the vessel. Important: The polymer beads should be sifted directly into the vortex of the stirred solvent to speed wetting-out and dispersion. Continuous low-shear agitation for periods of 1-12 hours, depending on the grade and concentration of resin, is recommended.

After the solution appears clear in the tank, a sample should be spread out on a Leneta card or glass. After the solvent evaporates and a film forms on the card or glass, there should not be any resin seeds. If there are any seeds, the tank should be agitated further to fully dissolve the resin. Tank agitation should not be stopped (except for sampling) until the film test indicates there are no resin seeds. Any cloudiness or residue may indicate that some polymer remains undissolved. The presence of water in the system can also cause cloudiness.

Solution time can be reduced by heating; most common solvents can be heated to approximately 49°C (120°F) without the need for reflux equipment. High-shear agitation also cuts dissolving time, but requires care to avoid overheating and excessive solvent loss.

## Solvent Solubility

Table depicts the solubility of Elvacite® 4028 at 30% solids in various solvents.

Solubility of Elvacite® 4028		
Solvent	Solubility	Rating
Acetone	S	C
Toluene	S	C
Methyl ethyl ketone	S	C
Dimethyl carbonate	S	C
Parachlorobenzotrifluoride	I	-
Methyl isobutyl ketone	S	C
n-Butyl acetate	S	C
t-Butyl acetate	I	-
Ethyl acetate	S	C
n-Propyl acetate	S	C
Methyl acetate	S	C
2-propanol	I	-
Low odor mineral spirits	I	-
<i>(C= Clear solution, S = Soluble, H = Hazy solution, I = Insoluble)</i>		

## Viscosity

The table below illustrates typical viscosities of Elvacite® 4028 in varying solvents at 30% solids.

Solvent	Viscosity (cP)
Acetone	954
Toluene	700
Methyl ethyl ketone	552
Dimethyl carbonate	794
Parachlorobenzotrifluoride	Insoluble
Methyl isobutyl ketone	2440
n-Butyl acetate	>15000
t-Butyl acetate	Insoluble
Ethyl acetate	2820
Methyl acetate	2620

## **COMPLIANCE WITH FDA REGULATIONS revised April 1, 2019**

**Pasadena, Texas, USA      Grade: ELVACITE® 4028**

**Issue date: December 2019**

We, MITSUBISHI CHEMICAL AMERICA, INC., Specialty Resins Division, confirm that Elvacite® 4028 complies with the compositional requirements of the following United States of America's Food and Drug Administration (FDA) regulations.

Elvacite® 4028 is cleared for use under the FDA 21 CFR 175.105 for adhesives used as components of articles intended for use in the packaging, transporting, or holding food.

Elvacite® 4028 is cleared for use under FDA 21 CFR 175.300 in resinous and polymeric coatings used as the food contact surface of articles intended for use in producing, packing, processing, preparing, treating, packaging, transporting, or holding food. The coating in its finished form in which it is to contact food is subject to a restriction on its chloroform soluble extractives.

Compliance with the limitation on extractives can only be demonstrated by tests carried out in the final article.

Elvacite® 4028 is cleared for use under FDA 21 CFR 175.320 in resinous and polymeric coatings for polyolefin films, provided it is intended for repeated food contact use as specified in FDA 21 CFR 175.300(a).

The coating in its finished form in which it is to contact food is subject to a restriction on its chloroform soluble extractives.

Compliance with the limitation on extractives can only be demonstrated by tests carried out in the final article.

Elvacite® 4028 is cleared for use under FDA CFR 176.170 as a component of the uncoated or coated food contact surface of paper and paperboard intended for use in producing, manufacturing, packing, processing, preparing, treating, packaging, transporting or holding aqueous and fatty foods.

Compliance with the limitation on extractives can only be demonstrated by tests carried out in the final article.

Elvacite® 4028 is cleared for use under FDA 21 CFR 176.180 as a component of the uncoated or coated food contact surface of paper and paperboard intended for use in producing, manufacturing, packing, processing, preparing, treating, packaging, transporting, or holding dry food.

Elvacite® 4028 is cleared under FDA 21 CFR 177.1010 as semirigid and rigid acrylic plastics articles intended for use in contact with food. The semirigid and rigid acrylic plastics in the finished form in which they are to contact food are subject to limitation on extractives

Compliance with the limitation on extractives can only be demonstrated by tests carried out on the final article.

**This statement of compliance is correct at the date of issue.**

**As food contact regulations and product formulations are subject to change, it is the user's responsibility to ensure that they are in possession of a current statement of compliance.**

# Pasadena, Texas, USA

Issue date: February 2022

Mitsubishi Chemical America, Inc., Specialty Resins Division hereby certifies that the country chemical inventory status of Elvacite® 4028 is as follows.

US	CA	AU	CN	KR	NZ	PH	TW	JP	Russian Federation	TH	Vietnam
TSCA	DSL	AIIC	IECSC	KECI	NZIoC	PICCS	TCSI	ENCS	Unified list of chemicals	DIW	NCI
Listed as Active	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y

Y: Listed

N: Not Listed

For further information or samples, please contact your local distributor, or:

## **Mitsubishi Chemical America, Inc.**

Specialty Resins Division  
9675 Bayport Blvd.  
Pasadena, Texas 77507  
Phone (713)758-8190  
[www.m-chem.com/specialtyresins](http://www.m-chem.com/specialtyresins)  
[MCA-SPR.sales@m-chem.com](mailto:MCA-SPR.sales@m-chem.com)

The recommendations, suggestions and data contained herein are believed to be true and accurate as of the time of printing. Mitsubishi Chemical America, Inc. does not represent, warrant or guarantee the completeness or reliability of the same, since the conditions of use, including in combination with other products, are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published Mitsubishi Chemical America, Inc. specifications for the warranty period if properly handled, and except as required by law, MITSUBISHI CHEMICAL AMERICA, INC. MAKES NO WARRANTIES, EXPRESS OR IMPLIED, ORAL OR WRITTEN, ARISING BY LAW, CONTRACT, STATUTE OR OTHER LEGAL THEORY OR OTHERWISE, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be defective during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.