

Great Lakes Chemical Corporation

PA

Business Unit or Division

Polymer Additives

One Great Lakes Boulevard, P.O. Box 2200, West Lafayette, IN 47996-2200

Document Type

Technical Information

Product Name

Great Lakes BC-58™

Halogenated Flame Retardant

Great Lakes BC-58 is a brominated, aromatic flame retardant for thermoplastic resin systems. **Great Lakes BC-58**, a white powder, offers excellent thermal stability, good UV stability and color in the final part.

Phenoxy-terminated carbonate oligomer of Tetrabromobisphenol A CAS Reg. Number [71342-77-3]

i ypicai	Fiohei	แษร
		Whit.

Appearance	White Powder
Bromine Content, %	58
Melting Range, ⁰ C	200 - 230
Specific Gravity @ 25 °C, g/ml Bulk Loose Density @ 25 °C, g/ml	2.2
Bulk Loose Density @ 25 ⁰ C, g/ml	0.66
Bulk Packed Density @ 25 °C, g/ml	1.02

Structure Proprietary

Thermogravimetric Analys	SIS (10 mg @ '	10 °C/minute	under №)
Weight Loss, %	5	10	50
Temperature, ⁰ C	380	423	475

Solubility (g/ 100 g Solvent)

Water	< 0.1	Toluene	14
Methylene Chloride	Complete	Methyl Ethyl Ketone	Complete
Methanol	< 0.1		

Great Lakes BC-58's unique combination of properties makes it a suitable flame retardant in PBT, PET, PBT/PET blends, PC, ABS, ABS/PC blends, Polysulfone and SAN. The UV stability of **Great Lakes BC-58** allows it to be formulated for applications subjected to indoor fluorescent and casual outdoor sunlight exposure. In addition, **Great Lakes BC-58's** high purity makes it a solid choice for applications requiring excellent electrical and thermal properties.

The use of proper protective equipment is recommended. Excess exposure to the product should be avoided. Wash thoroughly after handling. Store the product in a cool, dry, well-ventilated area away from incompatible materials. Unless stated, proper storage will permit usage of the product for 6 to 12 months from the date of receipt. For additional handling and toxicological information, consult the GLCC Material Safety Data Sheet.

The information supplied is presented in good faith and has been derived from sources believed to be reliable. Since conditions of use are beyond our control, all risks are assumed by the user. No representation is expressed or implied, and nothing herein shall be construed as permission or recommendation to practice a patented invention without license.