

SG1000 – Industrial Solvent

Rubber Compatibility

<u>RATING</u>	<u>RECOMMENDED AND APPROVED</u>
*A	Fluoroelastomer (FKM) - Viton
A	Epichlorohydrin (ECO/CO) - Hydrin
*AA	Fluoro Ethylene Propylene (FEP) - Teflon
A	Isobutylene Isoprene (IIR) - Butyl
A	Perfluorinated Elastomer (FFKM) - Chemraz
A	Perfluorinated Copolymer Elastomer (FFKM) - Kalraz
A	Fluorinated Copolymer (FXM) - Fluoraz
*A	Gylon - 3504, 3540, 3545, 3510 - Garlock Gylon

*Best for Service

NOT RECOMMENDED AND NOT APPROVED

NR	Nitrile (NBR) - Buna-N
NR	Nitrile (NBR) - Buna-N Blends
NR	Hydrogenated Nitrile (HNBR)
NR	Ethylene Acrylic (EAM) - (EA) - Vamac
NR	Chlorinated Polyethylene (CPE) (CM)
NR	Chlorosulfanated Polyethylene (CSM) - Hypalon
NR	Silicone (VMQ)
NR	Chloroprene or Polychloroprene (CR) - Neoprene
NR	Nitrile - Black (NBR)
NR	Nitrile - White (NBR)
NR	Styrene Butadiene (SBR) - Buna-S
NR	Polyacrylate (ACM)
NR	Polyurethane (AU) (EU)

Other SoyGold
Products:

Solvents

SG1000

SG1100

SC1500

SG2000

SG2500

CE 110

Fuels

Agriculture

NR	Polybutadiene or Butadiene (BR)
NR	Modified Polyethylene (AQP) - Aero Quip
NR	Synthetic Isoprene (IR) - Synthetic Rubber

NOT RECOMMENDED BUT MARGINAL

B	X-Link Polyethylene (XLPE)
B	Ethylene Propylene (EPDM)
B	Ethylene Propylene (EP)

[Return to SG1000](#)