



DuPont de Nemours, Inc.  
SALES SPECIFICATION

**Date Printed:** 2021-02-01

**Effective Date:** 2021-01-28

**Supersedes Date:**

**Name:** TEXTURECEL™ 30000 G Sodium Carboxymethylcellulose

**Specification Number:** 000001107714

**Previous Specified Material:** 00158839

**Final Testing Requirements**

Test and Test Condition	Limit	Unit	Method	Note
Active Content, dry basis <b>Test Frequency:</b>	99.00 Min audit basis	%	CE-55.4	
Substitution, degree of	0.82 — 0.95		CE-28.4	
Moisture Content, as packaged	8.0 Max	%	CE-7.1	
pH Value, 1% aqueous solution	6.5 — 8.5		CE-8.1	
Total salt content, dry basis <b>Test Frequency:</b>	1.00 Max audit basis	%	CE-15.4	
Viscosity, Brookfield, LVT, SP.4, 30 rpm, 1% aqueous sol. (dry basis), 25degC	3000 — 4000	mPa.s	CE-5.15	

READ PRECAUTIONARY INFORMATION AND MATERIAL SAFETY SHEETS. THIS PRODUCT IS SHIPPED IN COMPLIANCE WITH APPLICABLE LAWS AND REGULATIONS REGARDING CLASSIFICATION, PACKAGING, SHIPPING AND LABELING.

LAST PAGE