



FSE 7560

FSE 7560

Description

FSE 7560 is a fluorosilicone rubber, designed for calendaring, moulding and extrusion for a variety of solvent resistant applications. These products may be used with different peroxides and fillers to develop wide-ranging property profiles. This general purpose material is successfully used in a variety of automotive and aerospace applications, where a combination of excellent fluid-resistance with good overall mechanical properties, low-temperature performance and low compression set is required.

Key Features and Benefits

- Excellent Handling
- Blendable
- Easy pigmentable
- Broad fluid resistance
- Low compression set
- Low temperature flexibility
- Suitable for high temperature applications
- Constant physical properties over wide temperature range

Typical Physical Properties

Typical Properties of the Uncured Base Compound:			
Appearance			White
Density	DIN 53 479 A	g/cm ³	1.4
Typical Properties of the Vulcanized Rubber:			
100 phr FSE 7560 with 1,5 phr 2,5 Dimethyl-2,5 Di(t-butyl peroxy)Hexane(50%) Vulcanization conditions: 15 min. @ 177°C post cured: 4h @ 204°C in hot air			
Hardness	DIN 53 505*	Shore A	60
Tensile strength	DIN 53 504 S2*	N/mm ²	8,9
Elongation at break	DIN 53 504 S2*	%	300
Tear strength	ASTM D 624 die B	N/mm	26
"Compression set			
(22 h @ 177°C)*	DIN 53 517*	%	10
Rebound resilience	DIN 53 512*	%	24

* The quoted test methods are corresponding to ASTM standards.

Processing Recommendations

Various organic peroxides will vulcanize **FSE 7560** fluorosilicone compounds. Fabricators should make their selection of curing agents on the basis of method of fabrication, desired properties, and safety considerations. They are mixed into the rubber, if necessary together with **Silopren® HV**

Additives. The optimum cure cycle will depend on the method of processing used and the physical dimensions of the vulcanized product. Specific applications will require the use of air oven post cures.

Packaging

FSE 7560 is available in 22,7 kg and 454 kg boxes.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

The warranty period of FSE 7560 is 8 months if stored in the original unopened boxes and stored at dry conditions at room temperature (max. 43°C). The storage warranty period begins on the date of shipment

Customers should review the latest Material Safety Data Sheet (MSDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, and any special storage conditions required for safety. MSDS are available at www.momentive.com or, upon request, from any Momentive Performance Materials (MPM) representative. **For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center.** Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

From automotive to healthcare, from electronics to construction, products from Momentive Performance Materials Inc. are practically everywhere you look. We are a global leader in silicones and advanced materials with a 70+ year heritage of innovation and being first to market – with performance applications that improve everyday life. By knowing our customers' needs and creating custom technology platforms for them, we provide science based solutions to help customers increase performance, solve product development issues and engineer better manufacturing processes.

Contact Information

For product prices, availability, or order placement, contact our customer service by visiting www.momentive.com/Contacts

For literature and technical assistance, visit our website at: www.momentive.com

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.

DISCLAIMER

The information provided herein was believed by Momentive Performance Materials Inc. (collectively with its subsidiaries, "Momentive") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for user's intended application or use. All products supplied by Momentive are subject to Momentive's standard terms and conditions of sale. **MOMENTIVE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY MOMENTIVE,** except that the product shall conform to Momentive's specifications. Nothing contained herein constitutes an offer for the sale of any products.