

Technical Information

Introduction

Viton™ GFLT-200S* fluoroelastomer is a low viscosity 67% fluorine, peroxide-cured, low temperature fluoroelastomer. GFLT-200S utilizes the latest technology from Chemours, Advanced Polymer Architecture (APA), which includes a novel peroxide cure site along with an optimized molecular weight distribution.

Features

- Is ideal for blending with Viton™ GFLT-600S to reach intermediate viscosity ranges for injection and transfer molding
- Cures exceptionally fast to a high state of cure
- Improved mold release/mold fouling properties
- Improved mold flow and less shear sensitivity for a 25 Mooney peroxy-cured FKM
- Good physical properties with high elongation, both original and aged
- Improved water resistance/lower volume swell in water
- Excellent compression set resistance with either low or no post-cure

Processing

A load factor of 72%+ for internal mixing of GFLT-200S is preferred. The suggested process aids for GFLT-200S are 0.75 phr of Struktol® HT290, either alone or in combination with 0.5 phr of PAT-777, or combinations of 0.5 phr Armeen® 18D with carnauba wax or Struktol® WS280. The use of Diak™ 8 is NOT suggested, as it causes poor mold release and high compression set.

Diak™ 7 (TAIC) is the suggested coagent for all GFLT-200S compounds and usually used at a 3 phr level or lower, unless high modulus is needed. High levels of TAIC can bleed out and cause molding flaws. A peroxide level of 1.5–2 phr is suggested for this fast-curing FKM polymer.

Safety and Handling

Before handling or processing Viton™ GFLT-200S, read and be guided by the suggestions in the Chemours technical bulletin, "Handling Precautions for Viton™ and Related Chemicals."

Product Description

Chemical Composition	Copolymer of perfluoromethylvinyl ether, vinylidene fluoride, and tetrafluoroethylene with a cure site monomer
Physical Form	Sheet
Appearance	White to tan
Odor	None
Mooney Viscosity, ML 1 + 10 at 121 °C (250 °F)	25
Specific Gravity	1.86
Storage Stability	Excellent
Fluorine, %	~67

*Viton™ GFLT-200S was formerly named VTR-8555.

Table 1. General Properties of Viton™ GFLT-200S

Viton™ GFLT-200S	
ML-10 at 121 °C (250 °F) (gum)	27
Viton™ GFLT-200S	100
Zinc Oxide	3
N990 (MT Black)	30
Diak™ 7	3
Varox® DBPH-50	2
Total	138
Mooney Scorch at 121 °C (250 °F)	
Minimum	16
2 Pt. Rise, min	28.0
5 Pt. Rise, min	>30
10 Pt. Rise, min	—
ODR at 162 °C (324 °F), 3° Arc, 100 Range, 30 Min Clock	
M-L, dNm	6
ts-2, min	1.3
t'50, min	2.7
t'90, min	4.2
M-H, dNm	163
MDR 2000 at 177 °C (350 °F), 0.5° Arc, 100 Range, 6 Min Clock	
M-L, dNm	0.8
ts-2, min	0.4
t'50, min	0.6
t'90, min	1.1
t'95, min	1.3
M-H, dNm	32.2
Rosand Capillary Rheometer at 100 °C (212 °F), 1.5 mm die—L/D = 0/1 and 10/1	
<i>Shear Rate, sec⁻¹</i>	<i>Pressure (short die L/D = 0/1), MPa</i>
113	3.0
452	4.6
1,129	6.0
2,221	7.4
Spider Mold Flow Test—Sprue 0.8 mm (0.031 in)—Transfer Pressure 103 bar—(Cured 7 min at 177 °C [350 °F])	
Total Shot Weight, g	39.9
Weight of Spider, g	27.5
Fill Factor, %	69%
Physical Properties at RT—Original (Cured 7 min at 177 °C [350 °F])—No post-cure	
M-10, MPa	0.7
M-100, MPa	4.2
Tensile, MPa	9.7
T-B, psi	1,404
Elongation, %	226
Hardness, A, pts	68

continued

Table 1. General Properties of Viton™ GFLT-200S (continued)

Viton™ GFLT-200S	
"Hot" Tear Strength at 150 °C (302 °F)—Original (Cured 7 min at 177 °C [350 °F])—No post-cure	
Tear Die B (nicked), N/mm	5.5
Physical Properties at RT—Original (Cured 7 min at 177 °C [350 °F])—Post-cured 2 hr at 232 °C [450 °F] as noted	
M-10, MPa	0.9
M-100, MPa	5.3
Tensile, MPa	15.3
T-B, psi	2,213
Elongation, %	214
Hardness, A, pts	72
Physical Properties at RT—Heat Aged 70 hr at 250 °C (482 °F) in Oven	
M-100, MPa	4.0
% Change, M100	-24
Tensile, MPa	15.6
% Change, T-B	4
Elongation, %	264
% Change, E-B	27
Hardness, A, pts	74
Pts Change	2
Physical Properties at RT—Heat Aged 70 hr at 275 °C (527 °F) in Oven	
M-100, MPa	2.6
% Change, M100	-51
Tensile, MPa	9.4
% Change, T-B	-37
Elongation, %	380
% Change, E-B	83
Hardness, A, pts	71
Pts Change	-1
Physical Properties at RT—Aged 168 hr at 150 °C (302 °F) in ASTM #105 Oil (5W/30)	
M-100, MPa	5.3
% Change, M100	1
Tensile, MPa	9.5
% Change, T-B	-37
Elongation, %	157
% Change, E-B	-25
Hardness, A, pts	74
Pts Change	2
Volume Swell, %	0.4

continued

Table 1. General Properties of Viton™ GFLT-200S (continued)

Viton™ GFLT-200S	
Compression Set, Method B, O-Rings	
22 hr at 200 °C (392 °F)	
– No Post-cure	19
– Post-cured at 232 °C (450 °F)	13
70 hr at 200 °C (392 °F)	
– No Post-cure	22
– Post-cured at 232 °C (450 °F)	21
Low Temperature Testing	
TR-10, °C	-24.4
T _g by DSC, °C	-25.5
Volume Swell After Immersion—168 hr at temperature as noted	
Fuel C at 23 °C (73 °F)	6.3
CM15 (85/15 Fuel C/Methanol) at 23 °C (73 °F)	12.4
Methanol, 23 °C (73 °F)	8.8
Water at 100 °C (212 °F)	3.3

Table 2. Blend of Viton™ GFLT-200S and Viton™ GFLT-600S

	Viton™ GFLT-200S	Blend	Viton™ GFLT-600S
ML-10 at 121 °C (250 °F) (gum)	24	41	61
Viton™ GFLT-200S	100	50	—
Viton™ GFLT-600S	—	50	100
Zinc Oxide	3	3	3
MT Black (N-990)	30	30	30
DIAK™ 7	3	3	3
Varox® DBPH-50	2	2	2
Total	138	138	138
Mooney Scorch at 121 °C (250 °F)			
Minimum	16	25	36
2 Pt. Rise, min	26.7	22.2	20.0
5 Pt. Rise, min	27.6	23.7	21.2
10 Pt. Rise, min	>30	24.9	22.3
ODR at 162 °C (324 °F), 3° Arc, 100 Range, 30 Min Clock			
M-L, dNm	6	11	18
ts-2, min	1.5	1.2	1.2
t'50, min	2.9	2.6	2.5
t'90, min	4.2	4.1	4.2
M-H, dNm	169	167	161

continued

Table 2. Blend of Viton™ GFLT-200S and Viton™ GFLT-600S (continued)

	Viton™ GFLT-200S	Blend	Viton™ GFLT-600S
MDR 2000 at 177 °C (350 °F), 0.5° Arc, 100 Range, 6 Min Clock			
M-L, dNm	0.6	1.2	2.0
ts-2, min	0.4	0.4	0.4
t'50, min	0.6	0.6	0.6
t'90, min	1.0	1.0	1.0
t'95, min	1.3	1.2	1.2
M-H, dNm	35.2	33.6	32.4
Rosand Capillary Rheometer at 100 °C (212 °F), 1.5 mm die—L/D = 0/1 and 10/1			
	<i>Shear Rate, sec⁻¹</i>	<i>Pressure (short die L/D = 0/1), MPa</i>	
	113	4.0	5.2
	452	5.5	6.3
	1,129	6.7	7.3
	2,221	7.9	8.4
Physical Properties at RT—Original (Cured 7 min at 177 °C [350 °F]—No post-cure)			
M-100, MPa	5.0	5.1	4.7
Tensile, MPa	12.1	13.3	12.8
T-B, psi	1,759	1,929	1,862
Elongation, %	188	203	214
Hardness, A, pts	67	67	65
“Hot” Tear Strength at 150 °C (302 °F)—Original (Cured 7 min at 177 °C [350 °F]—No post-cure)			
Tear Die B (nicked), N/mm	8.1	7.5	8.5
Physical Properties at RT—Original (Cured 7 min at 177 °C [350 °F]—Post-cured 2 hr at 232 °C [450 °F])			
M-100, MPa	6.0	6.1	5.6
Tensile, MPa	16.8	16.9	16.6
T-B, psi	2,437	2,451	2,408
Elongation, %	198	199	206
Hardness, A, pts	70	68	67
Compression Set, Method B, O-Rings (2 hr post-cure)			
22 hr at 200 °C (392 °F)			
– No Post-cure	13	11	14
– Post-cured at 232 °C (450 °F)	9	9	11
70 hr at 200 °C (392 °F)			
– No Post-cure	20	20	20
– Post-cured at 232 °C (450 °F)	17	14	17
Low Temperature Testing			
TR-10, °C	-24.0	-24.8	-24.8
Tg by DSC, °C	-26.0	-26.1	-25.3

Test Procedures

Property Measured	Test Procedure
Compression Set	ASTM D395, Method B (25% deflection)
Compression Set, O-Rings	ASTM D395, Method B (25% deflection)
Hardness	ASTM D1414, durometer A
Mooney Scorch	ASTM D1646, small rotor at 121 °C (250 °F)
Mooney Viscosity	ASTM D1646, ten pass at 121 °C (250 °F)
ODR (oscillating disk rheometer)	ASTM D2084
Property Change After Heat Aging	ASTM D573
Stress/Strain Properties	
100% Modulus	
Tensile Strength (T-B)	ASTM D412, pulled at 8.5 mm/sec (20 in/min)
Elongation (E-B)	
Temperature Retraction (TR-10)	ASTM D1329
Volume Change In Fluids	ASTM D471

Test temperature is 23 °C (73 °F), except where specified otherwise.

For more information, visit Viton.com

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

© 2016 The Chemours Company FC, LLC. Viton™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: VTE-A10355-00-C0710

C-10953 (9/16)