# SP-1068

# Description

SP-1068 is a thermoplastic resin made from octylphenol and formaldehyde. It is typically used to increase tack in natural rubber and synthetic elastomers, including SBR, BR, IIR and IR.

## **General Product Data**

## **Product Specifications:**

Softening Point, Ball & Ring, (°C)	85-95
Acid Number	25-42
Test Methods available upon request	

## **Typical Properties:**

Specific Gravity	1.03
Viscosity, Gardner-Holdt, 64% in Toluene	K
Color, Gardner, 64% in Toluene	5
Form	Pellet

#### Solubility:

SP-1068 is soluble in aromatic and chlorinated hydrocarbons, ketones, esters and higher alcohols.

## Application

SP-1068 can be used as a stock additive to impart tack and used wherever tenacious bonds are necessary, especially with synthetic rubbers, which do not possess the inherent tack necessary for plied-up construction. In tire building, for example, plies, tread stock, and sidewalls must hold fast to the green tire until it is vulcanized or cured into an integral unit. For this application SP-1068 is typically used at 3-8 phr level.

## **Storage And Shelf Life**

SP-1068 should be stored where temperatures do not exceed 86 °F (30 °C) for long periods of time. For best results, it is recommended that this product be used within 1 year of manufacture date. As with all phenolic resins, SP-1068 will become darker with age. Pallets should never be stored double stacked.

**Note:** Resins of this type are known to agglomerate or sinter during storage. This condition does not affect the performance of the resin in its normal application and is not considered justification for rejection or return.

## Packaging

SP-1068 is packaged in lined Kraft bags and polyethylene bags. Standard weight is either 50 pounds or 25 kilograms

## Safety And Regulatory Information

For a current Safety Data Sheet (SDS) or other regulatory information, contact SI Group, Inc. at productinfo@siigroup.com.

The information contained herein is true to the best of our knowledge. SI Group, Inc. makes no warranty or guarantee of results and assumes no obligations or liabilities from the use of any products or processes mentioned herein. This publication is not to be taken as a license to operate under, or recommendation to infringe upon, any patents. © 2015 SI Group, Inc. All Rights Reserved.

