



Product Data Sheet

Epolene[®] E-14E Polymer

Application/Uses

- Automotive refinish
- Automotive
- Building and Construction
- Hot Melt Adhesives
- Pressure Sensitive Adhesives
- Solventborne Adhesives
- Waterborne Adhesives
- Wax Modification

Key Attributes

- Imparts slip resistance, durability, and toughness to floor finishes
- Low density polyethylene (PE)
- Oxidized to provide functionality
- Produces stable water based emulsions

Product Description

The *Epolene* E-14E is a low molecular weight, low density, oxidized polyethylene. The low molecular weight and low softening point contribute to the production of stable, low color emulsions by both atmospheric (wax-to-water) and pressure emulsification methods. *Epolene* E-14E imparts excellent slip resistance to floor polish films.

Typical Properties

Property	Test Method	Typical Value, Units
Polymer Type		Ox-PE
Acid Number (mg KOH/g)		17
Ring and Ball Softening Point	ASTM E 28	104°C
Penetration Hardness ^a	ASTM D 5	4 dmm
Viscosity, Brookfield @ 125°C (257°F)		225 cP
Molecular Weight ^b		3,600

^a Needle under 100-g load for 5s @ 25 deg C, tenths of mm

^b Molecular weight measured via Gel Permeation Chromatography (GPC) using polystyrene standards

Comments

Properties reported here are typical of average lots. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing

herein waives any of the Seller's conditions of sale.

Compatibility and Solubility

Epolene polymers are compatible with many polymers, resins, and natural and synthetic waxes.

Packaging

Epolene E-14E polymer is supplied as free-flowing pellets, packaged in multiwall paper bags with a polyethylene coated inner liner [22.67 kg (50 lb) net weight]. The bags are palletized and stretch wrapped to prevent contamination during storage and shipment. Many *Epolene* polymers are also shipped in a variety of bulk containers.

Epolene E-14E polymer is available in powder form as *Epolene* E-14EP polymer.

Storage

The useful life of this product can be affected by storage and handling conditions. When stored in the original unopened container in an enclosed area and protected from moisture, extreme temperatures and contamination, this product is estimated to continue to meet applicable sales specifications for more than 2 years from the date of manufacture. First in first out (FIFO) inventory control is recommended.