

**Product Description:**

Polybond® 3150 is a maleic anhydride grafted polypropylene recommended for coupling of glass and other fillers in polypropylene composites. It is also recommended as a compatibilizer for PP blends with polar polymers such as nylon and EVOH. Polybond® 3150 may also be used as a promoter for PP/metal adhesion.

**Physical Properties:**

<b>PROPERTIES</b>	<b>TYPICAL VALUES</b>	<b>METHOD</b>
Physical Form	Pellets	
Melt Flow Rate (230/2.16):	50 g/10 min	ASTM D-1238
Density at 23°C:	0.91g/cc	ASTM D-792
Maleic Anhydride Level:	0.5 weight %	
Melting Point:	160-170°C	(DSC)