

# ROYCO® 44

## ANTISEIZE COMPOUND

**ROYCO® 44** is a heavy-duty anti-seize compound Graphite And Technical Petrolatum developed for use on aircraft engine spark plugs, igniters, and threaded fasteners and fittings. ROYCO® 44 has a consistency similar to modeling clay and is black in color.

### APPLICATIONS

**ROYCO® 44** is recommended for use as an anti-seize compound for threaded fasteners, fittings as well as spark plugs, igniters, and similar threaded aircraft engine accessory requiring an electrically conductive anti-seize compound or torque aid. This compound may be safely used in contact with corrosion resistant metals such as austenitic stainless steels, titanium, nickel and cobalt alloys.

### FEATURES AND BENEFITS

#### Features

- **ROYCO® 44 contains graphite; it may be safely used in contact with austenitic corrosion-resistant steels, titanium, nickel, cobalt alloys, similar corrosion-resistant metals and alloys.**

### APPROVALS & SPECIFICATIONS

**ROYCO® 44** meets SAE AMS-2518B which supersedes MIL-T-5544C.

### COMPATIBILITY

Austenitic corrosion-resistant steels, titanium, nickel, cobalt alloys, and similar corrosion-resistant metals and alloys. Not compatible with aluminum, magnesium, ferrous, zinc and cadmium alloys or plated coatings.



PROPERTIES	TEST METHOD	ROYCO® 44
Worked Penetration, mm	ASTM D937	193
Stability	Para 4.5.1	Pass
Material	Para 3.1	Conforms

**PACKAGING**

**ROYCO® 44** is available in 24 x 1.75 lb cases. Other package sizes may be available on special request.

**LIMITATIONS**

Graphite may promote corrosion of aluminum, magnesium, ferrous, zinc and cadmium alloys or plated coatings. As such, **ROYCO® 44** should not be used with such metals. This compound is an electrical conductor. Apply light coating to lower spark plug threads only. The compound must not come into contact with spark terminals or electrodes. Do not use in oxygen systems - explosion may result!

A company of the  
**LANXESS**  
Group

The information contained herein relates to a specific Chemtura product and its use, and is based on information available as of the date hereof. Additional information relating to the product can be obtained from the pertinent Material Safety Data Sheets. NOTHING IN THIS TECHNICAL DATA SHEET SHALL BE CONSTRUED TO CONSTITUTE A REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, REGARDING THE PRODUCTS CHARACTERISTICS, USE, QUALITY, SAFETY, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall constitute permission or recommendation to practice any intellectual property without the permission of the owner.

The Chemtura logo is a trademark of Chemtura Corporation or one of its subsidiaries.

Copyright © 2016 Chemtura Corporation. All rights reserved.

**North America**

+1.800.325.6252  
customer.care@chemtura.com

**Europe, Middle East & Africa**

+44.161.875.3800  
emea.export@chemtura.com

**South & Central America**

+55.19.3522.5000  
Atendimento.cliente@chemtura.com

**Asia Pacific**

+86.21.3866.6509  
orders.apac@chemtura.com

