

ANDEROL® 5000 Series

Synthetic Gear and Bearing Oils, EP (Extreme Pressure)

DESCRIPTION

The ANDEROL® 5000 Series are a family of heavy duty gear and bearing lubricants formulated to provide excellent oxidation resistance, anti-wear, and EP properties. They are available in ISO grades 220, 320, 460, and 680. These fluids are fully compatible with petroleum based oils while offering excellent wear and rust protection, high viscosity index, high flash point, low pour point, outstanding oxidative stability, and cleaner running systems.

APPLICATIONS

- Particularly suited to heavy duty gear applications for extreme service conditions such as high impact loading
- All types of enclosed gear drives
- Bearings, including plain, rolling elements and antifriction types

ADVANATAGES

- Excellent oxidation and thermal stability
- Wide operating temperature range
- Lower maintenance costs
- Extended lubricant life
- · Improved cleanliness
- Very good rust and copper corrosion prevention
- Compatible with petroleum oils, therefore allowing minimal effort to changeover

APPROVALS and SPECIFICATIONS

Fives Cincinnati P-specifications (formerly MAG IAS, LLC and Cincinnati Machine)

P-74 (ISO 220), P-59 (ISO 320), P-35 (ISO 460), P-34 (ISO 680)

o GE Motorized Wheel D50E27

D50E27B (ISO 220), D50E27C (ISO 320), D50E27D (ISO 460), D50E27E (ISO 680)

Meets or exceeds the requirements of:

DIN 51517 part 3

ANDEROL® 5000 Series

TYPICAL PROPERTIES

		ANDEROL®	ANDEROL®	ANDEROL®	ANDEROL®
PROPERTIES	TEST METHOD	5220	5320	5460	5680
ISO Grade		220	320	460	680
AGMA Grade	AGMA 9005-D94	5EP	6EP	7EP	8EP
Viscosity, cSt					
@ 40°C	ASTM D445	233	334	460	722
@ 100°C	ASTM D445	28	36.8	47	65.2
Viscosity Index	ASTM D2270	156	157	160	161
Pour Point, °C	ASTM D97	-42	-42	-39	-36
Flash Point, °C	ASTM D92	268	270	278	287
Density @15.6°C (60°F)	ASTM D1250	0.85	0.86	0.86	0.86
Acid number, mg KOH/g	ASTM D664	0.74	0.75	0.70	0.75
Foam Seq I,II,III (ml/ml)	ASTM D892	0/0, 0/0, 0/0	0/0, 0/0, 0/0	0/0, 0/0, 0/0	0/0, 0/0, 0/0
Rust Test	ASTM D665B	Pass	Pass	Pass	Pass
4-Ball Wear, mm	ASTM D4172	0.37	0.35	0.35	0.32
4-Ball EP, Kg Weld	ASTM D2783	250	250	250	250
FZG pass load stage, A/8.3/90, fail stage min.	ASTM D5182	>12			

^{*} AGMA 9005-E02 significantly changed the viscosity grade nomenclature. With the change from the AGMA viscosity grade equivalents to ISO viscosity grade classifications, the designations S, EP, R and COMP are no longer be used as part of the viscosity grade nomenclature.

COMPATABILITY

ANDEROL synthetic hydrocarbon based lubricants are similar to mineral oils in their compatibility with paints, seals, gaskets and hoses. No special precautions related to compatibility are required when changing over from a mineral oil lubricant to an ANDEROL synthetic hydrocarbon based lubricant.

PACKAGING

ANDEROL® 5000 Series products are available in 5-gallon pails and 55-gallon drums. Other packages may be available upon request.

The physical properties listed are represented as "Typical". Information contained herein is considered accurate to the best of our knowledge. It is offered for your consideration and investigation, and is not to be construed as a representation or warranty expressed or implied. The "Typical" properties may vary slightly; and the fabricator or end user is responsible for insuring the suitability of our products for their specific application or end use. Refer to the Safety Data Sheet for this product for additional important information relating to the product and its use. The Technical Data Sheet is not intended to be, and should not be relied upon as, a substitute for the detailed health and safety information contained on the Safety Data Sheet. NO PART OF THIS TECHNICAL DATA SHEET CONSTITUTES AN EXPRESS OR IMPLIED REPRESENATION REGARDING THE CHARACTERISTICS, USE, QUALITY, SAFETY, MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE OF THE PRODUCT. ALL SUCH WARRANTIES ARE EXCLUDED EVEREST, ANDEROL, ROYCO, and PQ and their corresponding logos are characteristics of Chemtura Corporation or its affiliates. Copyright © 2014 Chemtura Corporation. All rights reserved.



Anderol Specialty Lubricants a division of Chemtura Corporation 215 Merry Lane East Hanover, NJ 07936 USA Technical Service +1.973.887.7410 Customer Service +1.203.573.4595 Fax +1.203.573,2324 www.anderol.com www.chemtura.com