


SILPLUS* 60 MP

ELASTOMER



Silplus 60 MP is a heat cured elastomer with outstanding processing capability. Silplus 60 MP heat cured elastomer when properly compounded and catalyzed may be considered for use in a wide variety of applications such as extrusion, molding and calendaring.

Key Features and Typical Benefits

- compounding simplicity
- good extrudability
- high mechanical properties
- good green strength
- easily blendable
- versatile

Potential Applications

Because of its outstanding properties, Silplus 60 MP heat cured elastomer is an excellent candidate for most types of molding, extrusion and calendaring applications.

Typical Physical Properties

Typical Properties of the Uncured Base Compound

Appearance			Translucent
Density, 23°C	DIN 53 479 A	g/cm ³	1.17
Mooney Viscosity	DIN 53 523		
ML (4) 25°C		ME	39
Δ ML 0/ML4		ME	≤ 20

Typical Properties of the Vulcanized Rubber
100 (pbw) Silplus 60 MP heat cured elastomer with 0.4 (pbw) like 2,5-Dimethyl-2,5-di(tert.butylperoxy)hexane (100%).
Vulcanization conditions: 10 min. @ 170°C.

Hardness	DIN 53 505	Shore A	60
Tensile Strength	DIN 53 504 S2	N/mm ²	11
Elongation at Break	DIN 53 504 S2	%	500
Tear Strength	ASTM D 624 die B	N/mm	28
Compression Set (22 h @ 175°C)	ISO 815	%	25

Typical Properties of the Vulcanized Rubber
100 (pbw) Silplus 60 MP heat cured elastomer with 1.2 (pbw) bis-(2,4-dichlorobenzoyl)-peroxide (50%).
Vulcanization conditions: 10 min. @ 120°C. Post cured: 4h @ 200°C.

Hardness	DIN 53 505	Shore A	61
Tensile Strength	DIN 53 504 S2	N/mm ²	12
Elongation at Break	DIN 53 504 S2	%	490
Tear Strength	ASTM D 624 die B	N/mm	26

Typical data are average data and actual values may vary.
Typical data shall not be used as product specifications.

SILPLUS* 60 MP

Regulatory Compliance

BfR:

The ingredients are listed in the BfR recommendation XV "Silicones"⁽¹⁾

FDA:

Compositionally Compliant with the requirements of 21 CFR 177.2600 – Rubber articles intended for repeated use and have been found, through testing of a representative sample, to meet the extractives limitations in 21 CFR 177.2600(e) and/or (f). - Note a

Biocompatibility:

A representative sample of Silplus 60 MP has passed USP Class VI (United State Pharmacopeia 32, National Formulary 27, 2009. <88> Biological Reactivity Test, In Vivo tests) and ISO 10993 (Part 6, 10, and 11) tests using Good Laboratory Practices (GLP). - Note b.

Drinking Water Compliance:

KTW and WRAS approved product (BS 6920)

In compliance with the requirements of the DVGW working sheet W 270

Flammability Test:

Listed as UL 94 HB (file No. E205753)

(1) Producer of the final article needs to test and confirm that the final product meets the extraction limits of BfR XV or corresponding EU legislation.

Note a: It is the responsibility of the user to determine that the final product complies with the extractive limitations and other requirements of 21 CFR 177.2600 under their specific manufacturing procedures.

Note b: Please contact Product Stewardship and Regulatory Group for details.

Packaging

Silplus 60 MP heat cured elastomer is available in 500 kg boxes.

General Instructions for Use

Various organic peroxides will vulcanize the compounding bases. Fabricators should select a curing agent based on the method of fabrication, desired properties and safety considerations. They are mixed into the rubber on a two-roll-mill, together with additives if necessary.

If the goods are to be vulcanized without pressure, e.g. in hot air or in an infrared radiation tunnel, bis-2,4-dichlorobenzoyl-peroxide (50%) is usually recommended. The dosage ranges from 1-2 parts (pbw) of cross-linking agent on 100 parts (pbw) of base compound. Good results have been achieved with a dosage of 1.5 parts (pbw). While the cross-linking agent is being incorporated, the temperature of the compound should not exceed 40°C to avoid scorch. Therefore the mixer or mill should always be well cooled.

To vulcanize goods in a press or in steam, dicumyl peroxide (95%) or 2,5-Dimethyl-2,5-di(tert.butylperoxy)hexan is generally recommended. Dicumyl peroxide crystals need to be melted in the rubber to become homogeneous and effective.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage conditions required. Material Safety Data Sheets are available at www.momentive.com or, upon request, from any Momentive Performance Materials representative. Use of other materials in conjunction with Momentive Performance Materials products may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Emergency Service

Momentive Performance Materials maintains an around-the-clock emergency service for its products.

<u>Location</u>	<u>Emergency Service Provider</u>	<u>Emergency Contact Number</u>
Mainland U.S., Puerto Rico	CHEMTREC	1-800-424-9300
Alaska, Hawaii	CHEMTREC	1-800-424-9300
Canada	CHEMTREC	1-800-424-9300
Europe, Israel	NCEC	+44 (0) 1235239670
Middle East	NCEC	+44 (0) 1235239671
Asia Pacific (except China)	NCEC	+44 (0) 1235239670
China	NCEC	+86-10-5100-3039
Latin America (except Brazil)	NCEC	+44 (0) 1235239670
Brazil	SOS Cotec	08000111767 or 08007071767
All other locations world wide	NCEC	+44 (0) 1235239670
At sea	Radio U.S. Coast Guard in U.S. waters NCEC in International waters	+44 (0) 1235239670

For Health related calls, contact Momentive Performance Materials at +1-518-233-2500 (English only).

DO NOT WAIT. Phone if in doubt. You will be referred to a specialist for advice.

Customer Service Centers

Worldwide Hotline

T +1 800 295 2392 / +1 607 786 8131
F +1 607 786 8309

North America

cs-na.silicones@momentive.com

Silicones – Fluids, Urethane Additives, Silanes, Specialty Coatings, RTVs and Elastomers

T +1 800 523 5862 / +1 800 334 4674
F +1 304 746 1654 / +1 304 746 1623

Consumer Sealants/ Construction Sealants and Adhesives

T +1 877 943 7325
F +1 304 746 1654

Latin America

cs-la.silicones@momentive.com

South America

T +55 11 4534 9650
F +55 11 4534 9660

Mexico and Central America

T +52 55 2169 7670
F +52 55 2169 7699

Europe, Middle East, Africa and India

cs-eur.silicones@momentive.com

T +00 800 4321 1000 / +40 21 3111848

Pacific

cs-ap.silicones@momentive.com

China

T +800 820 0202 / +86 21 3860 4892

Japan

T +0120 975 400 / +81 276 20 6182
F +81 276 31 6259

Korea

T +82 2 6201 4600
F +82 2 6201 4601

Malaysia

T +60 3 9206 1555
F +60 3 9206 1533

Thailand

T +66 2207 3456
F +66 2207 3488

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS. EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Silplus is a trademark of Momentive Performance Materials Inc.

The Momentive logo is a trademark of Momentive Performance Materials Holdings LLC.



22 Corporate Woods Boulevard
Albany, NY 12211 USA
+1 800 295 2392
+1 607 786 8131
momentive.com