

TRILENE® Liquid Polymers

Crompton Corporation, Uniroyal Chemical Technical Sales Service Center
Spencer Street, Naugatuck, CT 06770 USA (800) 243-5098 (203) 720-6659 Fax (203) 720-6204 www.cromptoncorp.com

TRILENE® 77

An Ethylene-Propylene-Ethylidene Norbornene Low Molecular Weight Polymer

Typical Properties

Appearance at Room Temperature	Pale Yellow, Waxy Solid
Ash	<0.1%
Volatiles 100°C (212°F)	<0.5%
Specific Gravity	0.86
Molecular Weight (Viscosity Average)	7500
Brookfield Viscosity (cps, RVT #7)	
@ 60°C (140°F)	800,000
@ 100°C (212°F)	102,000
Melting Transition by DSC, °C	45-50
Degree of Unsaturation	
Diene, %	10.5
Type	ENB
Ethylene/Propylene	75/25

TLJ
6/2002
T77.pdf

The recommendations for the use of our products are based on tests believed to be reliable. However, we do not guarantee the results to be obtained by others under different conditions. Nothing in this bulletin is intended as a recommendation to use our products so as to infringe on any patent

Crompton
Uniroyal Chemical