





# ATOFINA

## Technical Data

02445

### DIMETHYLAMINO-2-PROPANOL



#### SPECIFICATIONS

Color APHA	200 Maximum
DMA-2-P	99.0% Minimum
Water	0.25% Maximum
Clarity	No Turbidity or Suspended Matter

The above specifications are determined according to ATOFINA Chemicals analytical methods.

#### PROPERTIES

Form	Liquid
Coefficient of Cubical Expansion/ °C	0.00109
Flash Point, °F (TAG Closed Cup)	82
Molecular Weight	103.2
Average Weight, Pounds Per Gallon at 68 °F (20 °C)	7.08
Viscosity @ 20 °C	1.5
Vapor Pressure at 20 °C, mm Hg	8
Freezing Point, °C	-85
Specific Gravity @ 20/20 °C	0.845 - 0.855
Boiling Range, °C	121.0 - 127.0
Refractive Index at 20 °C	1.420 approximately

#### SAFETY

**BEFORE HANDLING THIS MATERIAL, READ AND UNDERSTAND THE MSDS (MATERIAL SAFETY DATA SHEET) FOR ADDITIONAL INFORMATION ON PERSONAL PROTECTIVE EQUIPMENT AND FOR SAFETY, HEALTH AND ENVIRONMENTAL INFORMATION.**



# ATOFINA

## Technical Data

### SHIPPING

#### Description on Shipping Papers:

Drums: Amines, Liquid, Corrosive, Flammable NOS (Dimethylamino-2-Propanol); 8 Corrosive Material; UN 2734; PG II; 3; Chemicals, NOIBN.

#### Containers (included and nonreturnable):

Size	Type	Material ID	Product Code	Net	Tare
55 gal. drums	55G TH UL	2429	02445-20	385 lbs.	37 lbs.

### MISCELLANEOUS:

CAS No.: 108-16-7  
HTS No.: 2922.19.60  
ECIN: 118423  
EINECS: 203-556-4

Effective: 11/1/99  
Supercedes: 8/15/96

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ATOFINA Chemicals expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein should be taken as an inducement to infringe any patent and the user is advised to take appropriate steps to be assured that any proposed use of the product will not result in patent infringement.