



5955 Scenic Highway • Baton Rouge, LA 70805-2044
800 / 535-9960 • www.lioncopolymer.com

Royalene® EPDM Product Data

Page 1 of 1

Issued 06/22/2006
Revised 12/06/2006

CELOGEN® AZ-130

Azodicarbonamide

TEST	MINIMUM	MAXIMUM	TEST METHOD
Decomposition Point, °C	205	213	ZM1025
*Ash, %	---	1.0	ZS1005
Heat Loss, %	---	0.3	ZS1008B
Alkali Insolubles, %	---	0.3	ZM 1017G
Average Particle Diameter, micrometers (microns)	3	4	Laser diffraction
Retained on 325 Mesh Screen, %	---	0.1	ZS 1037G
Color	Yellow - orange		ZS 1002
Appearance	Powder		ZS 1002B

* Contains silica flow conditioner

Notice: All information supplied by or on behalf of Lion Copolymer in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Copolymer assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use made of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Lion Copolymer for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.