


Butyl Acrylate

Acrylic acid ester, for manufacturing polymers and for use as a feed stock for syntheses



CAS No.: 141-32-2
EINECS No.: 205-480-7

Molecular formula

C₇H₁₂O₂

Molar mass: 128.2 kg/kmol

Product specification

Assay (Gas chromatography)	min. 99.50 %
Water content (ASTM E 203)	max. 0.050 %
Acid content (calc. as acrylic acid) (ASTM D 1613)	max. 0.0100 %
Color on dispatch (APHA, ASTM D 1209)	max. 10
Standard stabilization (ASTM D 3125 or HPLC)	15 ± 5 ppm MEHQ

The aforementioned data shall constitute the agreed contractual quality of the product at the time of passing of risk. The data are controlled at regular intervals as part of our quality assurance program. Neither these data nor the properties of product specimens shall imply any legally binding guarantee of certain properties or of fitness for a specific purpose. No liability of ours can be derived therefrom.

Other properties

Appearance	clear, colorless
Physical form	liquid
Odor	pungent
Density at 20 °C	0.898 g/cm ³
Refractive index n _D at 20 °C	1.4185
Boiling point	approx. 148 °C
Freezing point	approx. -64 °C
Viscosity at 25 °C	0.92 mPa · s
Specific heat of liquid	1.93 kJ/(kg · K)
Heat of evaporation at boiling point	292 kJ/kg
Heat of polymerization	504 kJ/kg
Vapor pressure	
at 0 °C	1.4 mbar
at 20 °C	5.4 mbar
Temperature rating for electrical equipment	T 3 (200-300 °C)

Labelling according to local Directives

see SDS

Applications

Butyl Acrylate forms homo- and copolymers. Copolymers of Butyl Acrylate can be prepared with acrylic acid and its salts, amides and esters, methacrylates, acrylonitrile, maleates, vinyl acetate, vinyl chloride, vinylidene chloride, styrene, butadiene, unsaturated polyesters, and drying oils. Butyl Acrylate is also an important feedstock for chemical syntheses because it readily undergoes addition reactions with many organic and inorganic compounds.

Storage & Handling

In order to prevent polymerization, Butyl Acrylate must always be stored under air, and never under inert gases. The presence of oxygen is required for the stabilizer to function effectively. It has to contain a stabilizer and the storage temperature must not exceed 35 °C. Under these conditions, a storage stability of one year can be expected upon delivery. In order to minimize the likelihood of overstorage, the storage procedure should strictly follow the "first-in-first-out" principle. For extended storage periods over 4 weeks it is advisable to replenish the dissolved oxygen content.

Storage tanks and pipes should be made of stainless steel or aluminum. Although Butyl Acrylate does not corrode carbon steel, there is a risk of contamination if corrosion does occur.

Regulations for the storage of flammable liquids must be observed (explosion-proof electrical equipment, vented tanks with flame arresters etc.). Storage tanks, pumps and pipes must be earthed.

For more detailed information please consult also the brochure "SAFE HANDLING AND STORAGE OF ACRYLIC ESTERS" of EBAM.

Safety

A Safety Data Sheet has been compiled for Butyl Acrylate that contains up-to-date information on questions relevant to safety.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

November 2020