

# **Product Data Sheet**

## Eastman Cellulose Acetate Butyrate (CAB-381-0.1)

## Application/Uses

- Coatings for Automotive Plastics
- Coatings for plastic
- Coatings
- Lacquers for automotive
- Lacquers
- Nail care
- Printing Inks
- Truck/Bus/Commercial Vehicles

### **Product Description**

Eastman Cellulose Acetate Butyrate (CAB 381-0.1) is a cellulose ester with medium butyryl content and low viscosity. It was designed for use where low-application viscosities at relatively high solids levels is needed. It is soluble in a wide range of solvents and compatible with many other resins. It will also tolerate the use of solvent blends currently exempt from certain air pollution regulations. It is supplied as a dry, free-flowing powder.

# **Typical Properties**

Property	Typical Value, Units
Butyryl Content	37 wt %
Acetyl Content	13 wt %
Hydroxyl Content	1.5%
Viscosity <sup>a</sup>	0.38 poise
Color b	50 ppm
Haze <b>b</b>	15 ppm
Acidity as Acetic Acid	0.03 wt %
Ash Content	<0.01%
Refractive Index	1.48
Heat Test @ 160°C for 8 hr	Tan melt
Melting Point	155-165°C
Specific Gravity	1.2
Wt/Vol (Cast Film)	1.2 kg/L (10.0 lb/gal)
Bulk Density	
Poured	458.1 kg/m³ (28.6 lb/ft³)
Tapped	544.5 kg/m³ (34 lb/ft³ )
Dielectric Strength	787-984 kv/cm (2- 2.5 kv/mil)
	123°C

Glass Transition Temperature  $(T_q)$ 

Molecular Weight <sup>c</sup> M <sub>n</sub>	20000
Tukon Hardness	18 Knoops

<sup>&</sup>lt;sup>a</sup> Viscosity determined by ASTM Method D 1343. Results converted to poises (ASTM Method D 1343) using the solution density for Formula A as stated in ASTM Method D 817 (20% Cellulose ester, 72% acetone, 8% ethyl alcohol).

#### **Comments**

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

22-Aug-2006 2:34:17 PM

b Determination of color and haze made on a solution of the cellulose ester dissolved in MIBK using Pt-Co color standards and Johns-Manville Celite (diatomaceous silica products) haze standards.

<sup>&</sup>lt;sup>c</sup> Polystyrene equivalent number average molecular weight determined by gel permeation chromatography.