

Technical Data Sheet

Eastman™ Chlorinated Polyolefin 343-3 (25% Solids in Xylene)

Applications

- Auto oem
- Auto refinish
- Automotive
- Automotive parts & accessories
- General industrial coatings
- Graphic arts
- Non-medical housings & hardware for elec
- Protective coatings
- Truck/bus/rv

Product Description

Eastman™ Chlorinated Polyolefin 343-3 (25% Solids in Xylene) is 26-32 wt. % chlorine and has a Gardner color value of 6 - 7. Chlorinated Polyolefin 343-3 has a good solvent tolerance for a wide range of solvents.

Typical Properties

Property	Test Method	Typical Value, Units
General		
Specific Gravity @ 25°C/25°C		0.906
Flash Point Tag Closed Cup		23 °C (74 °F)
Fire Point		36 °C (97 °F)
Color, Gardner		6-7
Autoignition Temperature	D 2155	>538 °C (>1000 °F)
Chlorine		26-32 wt %
Specific Gravity, Solid CPO @ 25°C/25°C		1.108

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

2/28/2018 11:35:39 AM