



## Product Data Sheet

### Eastman™ Chlorinated Polyolefin 515-2 (40% in Aromatic 100)

#### Application/Uses

- Adhesion promoter for inks
- Automotive OEM
- Coatings
- Coatings for Automotive Plastics
- Coatings for plastic
- Inks
- Printing Inks

#### Product Description

Eastman™ Chlorinated Polyolefin 515-2 (40% in Aromatic 100) is a liquid at room temperature. If the solution gels due to storage at low temperatures, it can be re-liquified by warming to 38 degrees C with agitation. CP 515-2 has good heat resistance. Solutions of CP 514-2 (as supplied) can easily be reduced with xylene, toluene, selected ketones, and ester solvents. CP 515-2 is compatible with a variety of resins. It combines with the resins to give clear solutions and deposit clear films. Although CP 515-2 shows borderline compatibility with some resins, this is not a problem because of the small amount of CP 515-2 usually added to a coating or ink. CP 515-2 has excellent adhesion to polypropylene and good to excellent adhesion to many other substrates. Not only will CP 515-2 adhere to a variety of substrates, but when added to coatings and inks, it improves their adhesion to these substrates.

#### Typical Properties

Property	Typical Value, Units
Specific Gravity @ 25°C/25°C	0.944
Flash Point Tag Closed Cup	41°C (107°F)
Color, Gardner	7
Chlorine	26-32 wt %
Specific Gravity, Solid CPO @ 25°C/25°C	1.04-1.09

#### Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

*Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

