



Product Data Sheet

Eastman CP 730-1 Chlorinated Adhesion Promoter (100% Solids)

Application/Uses

- Automotive OEM
- Coatings for Automotive Plastics
- Automotive refinish
- Automotive
- Truck/Bus/Commercial Vehicles

Key Attributes

- Excellent adhesion to TPO and PP plastics
- Excellent humidity resistance
- Outstanding gasoline and gasohol resistance

Product Description

Eastman CP 730-1 Chlorinated Adhesion Promoter is designed to be the active component in adhesion promoter primers used to insure adhesion of color coats and topcoats to polypropylene (PP) and thermoplastic olefin (TPO) plastics.

Eastman CP 730-1 provides excellent adhesion properties for all typical basecoat chemistries. Adhesion promoters built around CP 730-1 exhibit excellent gasoline resistance and humidity resistance, required for the newer, high modulus TPOs being used today. CP 730-1 also provides outstanding gasoline and gasohol resistance.

Eastman CP730-1 Chlorinated Adhesion Promoter is also available at 20% weight solids in aromatic 100 or in xylene.

Typical Properties

Property	Typical Value, Units
Physical Form	Soild (granules)
Color	Beige
Specific Gravity	> 1
Softening Point	> 100°C
Flash Point	Not applicable, combustible solid
Chlorine	20.5-23.5%
Solubility in Water	Negligible

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

19-Jul-2005 1:59:05 PM