



# **Technical Data Sheet Eastman™ MTBHQ**

### **Applications**

- Acrylic acid
- · Commerical printing inks
- Intermediates
- · Kitchen & bath
- · Molding & trim interior
- · Paints & coatings
- Photographic supplies
- Protective coatings

#### **Product Description**

Eastman™ MTBHQ (mono t-butyl hydroquinone) is a light tan solid. Eastman™ MTBHQ is used primarily as a polymerization inhibitor and industrial antioxidant. Its higher solubility and increased potency at higher temperartures combine to make it more useful in many applications than unsubstituted hydroquinone. The hindered hydroxyl group also makes Eastman™ MTBHQ an interesting organic intermediate.

## **Typical Properties**

Property	Typical Value, Units	
General		
Molecular Weight	166.22	
Empirical Formula	$C_{10}H_{14}O_2$	
Appearance	Light tan solid	
Assay	98 wt % min.	
Specific Gravity		
@ 20°C/20°C	1.05	
Melting Point	125 °C	
Boiling Point	295 °C	
Flash Point		
Cleveland Open Cup	171 °C (340 °F)	
Autoignition Temperature	457 °C (855 °F)	
Solubility @ 25º (77ºF)		
In Acetone	66 wt %	
In Ethanol (95%)	> 60 wt %	
In Ethyl Acetate	50 wt %	
In Styrene	< 5 wt %	
In Toluene	Insoluble	
in Water	Moderate	

#### Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing

2/28/2018 11:35:39 AM

© 2023 Eastman Chemical Company or its subsidiaries. All rights reserved. As used herein, ® denotes registered trademark status in the U.S. only.